## **CLAIMS**

What is claimed is:

 A creep resistant, castable magnesium alloy comprising, by weight: between about 3% and about 10% aluminum;

between about 0.5% and about 2.5% calcium;

up to about 1.5% silicon;

up to about 0.7% zinc;

the balance being magnesium, except for impurities commonly found in magnesium alloys.

- 2. The alloy of claim 1 further comprising up to about 1% by weight tin.
- 3. The alloy of claim 1 further comprising up to about 2.0% by weight of rare earth metals.
- 4. The alloy of claim 1 wherein the weight percentage of aluminum is between about 4.5% and about 5.5%.
- 5. The alloy of claim 1 wherein the weight percentage of aluminum is about 5%.

- 6. The alloy of claim 1 wherein the weight percentage of calcium is between about 1.5% and about 2.5%.
- 7. The alloy of claim 1 wherein the weight percentage of calcium is about 2%.
- 8. The alloy of claim 1 wherein the weight percentage of silicon is between about 0.3% and about 0.7%.
- 9. The alloy of claim 1 wherein the weight percentage of silicon is about 0.7%.